



Greases Key Range

Greases Key Range		Grade NLGI	Base Oil Viscosity @ 40 °C	Operating Temperature	Load	Adhesiveness	Water Resistance	Pumpability	Mechanical Stability	Speed Property
BIO	BIOADHESIVE PLUS	1	190	-20 °C to +90 °C	••	••••	••••	••	••	Low
	BIOMERKAN RS	3	32	-20 °C to +90 °C	•	••	••••	•	•••	Med
	BIOMULTIS EP 2	2	150	-30 °C to +140 °C	••	•	•	•••	••	Med

Greases Key Range		Grade NLGI	Base Oil Viscosity @ 40 °C	Operating Temperature	Load	Adhesiveness	Water Resistance	Pumpability	Mechanical Stability	Speed Property
Lithium Calcium	MULTIS EP 00	00	173	-30 °C to +100 °C	•	•	••	••••	•	Med
	MULTIS EP 0	0	190	-30 °C to +100 °C	•	•	••	••••	•	Med
	MULTIS EP 1	1	190	-30 °C to +120 °C	•	••	••	•••	••	Med
	MULTIS EP 2	2	190	-25 °C to +120 °C	•	••	••	•••	••	Med

Greases Key Range		Grade NLGI	Base Oil Viscosity @ 40 °C	Operating Temperature	Load	Adhesiveness	Water Resistance	Pumpability	Mechanical Stability	Speed Property
Lithium	MARSON WR2	2	500	-10 °C to +120 °C	••••	••••	•••	••	••	Low
	MULTIS XHV 2	2	1300	-20 °C to +130 °C	••••	••••	•••	••	••	Low

Greases Key Range		Grade NLGI	Base Oil Viscosity @ 40 °C	Operating Temperature	Load	Adhesiveness	Water Resistance	Pumpability	Mechanical Stability	Speed Property
Lithium Complex	MULTIS COMPLEX EP 2	2	165	-20 °C to +160 °C	••	•	••	•••	••	Med
	MULTIS COMPLEX HV 2 Moly	2	360	-30 °C to +160 °C	•	•••	••	•••	••	High
	MULTIS COMPLEX XHV 2 Moly	2	800	-20 °C to +160 °C	••••	•••	••	•	••	Low
	MULTIS COMPLEX SHD 100	2	100	-50 °C to +160 °C	••	•	••	•••	••	High
	MULTIS COMPLEX SHD 220	2	220	-40 °C to +160 °C	••	•	••	•••	••	Med
MULTIS COMPLEX SHD 460	1.5	460	-40 °C to +160 °C	•••	•••	••	••	••	Low	

Load

NSF Food Grade

Biodegradable

Adhesiveness

Synthetic

with MoS2

Graphite

Water Resistance

Standard

Good

Excellent

Outstanding

Pumpability

Mechanical Stability

Speed Property

Drum 208L

Keg 60L

Pail 19-20L

Cartridge

Greases Key Range		Grade NLGI	Base Oil Viscosity @ 40 °C	Operating Temperature	Load	Adhesiveness	Water Resistance	Pumpability	Mechanical Stability	Speed Property
Calcium Sulfonate Complex	CERAN AD PLUS	0.5	1700	-20 °C to +150 °C	•••	••••	••••	••	•••	Low
	CERAN MS	1.5	650	-20 °C to +180 °C	•••	••	••••	••	•••	Low
	CERAN XM 100	1.5	100	-30 °C to +180 °C	•••	•	••••	•••	•••	Med
	CERAN XM 220	1.5	220	-30 °C to +180 °C	•••	•	••••	•••	•••	Low
	CERAN XM 220 Moly	1.5	220	-30 °C to +180 °C	••••	•	••••	•••	•••	Med
	CERAN XM 460	1.5	460	-25 °C to +180 °C	•••	••	••••	••	•••	Low
	CERAN XS 40 Moly	1.5	40	-60 °C to +135 °C	••••	•	••••	•••	•••	High
	NEVASTANE XS 80	NSF 1.5	80	-55 °C to +180 °C	•••	•	••••	•••	•••	High
	NEVASTANE XS 220	NSF 1.5	220	-35 °C to +180 °C	•••	•	••••	•••	•••	Med
	NEVASTANE XS 320	NSF 1.5	320	-40 °C to +180 °C	•••	•	••••	•••	•••	Med

Greases Key Range		Grade NLGI	Base Oil Viscosity @ 40 °C	Operating Temperature	Load	Adhesiveness	Water Resistance	Pumpability	Mechanical Stability	Speed Property
Aluminum Complex	NEVASTANE XMF 00	NSF 00	120	-20 °C to +150 °C	••	•	•••	•••	••	High
	NEVASTANE XMF 0	NSF 0	120	-20 °C to +150 °C	••	•	•••	•••	••	High
	NEVASTANE XMF 1	NSF 1	120	-20 °C to +150 °C	••	••	•••	•••	••	High
	NEVASTANE XMF 2	NSF 2	120	-20 °C to +150 °C	••	••	•••	•••	••	High
	COPAL OGL 0	0/00	>1000	-20 °C to +150 °C	••••	••••	••••	•••	••	Low
	COPAL SPRAY (AEROSOL)	1	N/A	-30 °C to +120 °C	••••	••••	••••	N/A	••	Low

Greases Key Range		Grade NLGI	Base Oil Viscosity @ 40 °C	Operating Temperature	Load	Adhesiveness	Water Resistance	Pumpability	Mechanical Stability	Speed Property
Polyurea	ALTIS EM 2	2	110	-20 °C to +160 °C	•	•	••	••	••	High
	ALTIS SH 2	2	80	-40 °C to +180 °C	•	•	••	•••	••	High

Greases Key Range		Grade NLGI	Base Oil Viscosity @ 40 °C	Operating Temperature	Load	Adhesiveness	Water Resistance	Pumpability	Mechanical Stability	Speed Property
Clay Base	CALORIS 23	2.5	500	-15 °C to +220 °C	••••	••	••	•	••••	Low